


TWIN PORTS TESTING INC.

SINCE 1972



1301 NORTH THIRD STREET
SUPERIOR, WISCONSIN 54880

728 GARFIELD AVENUE
DULUTH, MINNESOTA 55802

8 INDUSTRIAL PARK ROAD
NEGAUNEE, MICHIGAN 49866

FUEL/ASH ANALYSIS REPORT

MATERIAL:	DATE: 1/10/94	TPT LAB NO: 116-84-C
WOODFIRE BRIQUETS		
ANALYSIS:	MOISTURE FREE	AS FIRED (REC'D)
% VOLATILE	82.06	77.78
% ASH	0.25	0.24
% FIXED CARBON	17.69	16.77
% SULPHUR	0.03	0.03
BTU PER LB	8,684	8,232
MOISTURE AND ASH FREE BTU/LB		8,706